

Code: TRO0

	■ Technical properties	Standards
Weave	NET	
Weave density (warp/weft)	6,2/5,2 yarn	UNI 1049/2
Weight	560 gr/m2	UNI 9213/3
Thickness	1 mm	
Height	Min 140 cm - Max 235 cm	
Thermo-fixing	Yes	
	■ Physical properties	
Breaking load (warp / weft)	2600 N/5cm - 2250 N/5cm	UNI EN ISO 1421
Breaking elongation (warp / weft)	22% - 17%	UNI EN ISO 1421
Elongation under 200 N (warp / weft)	3,2% - 1,3%	UNI EN ISO 1421
Fatigue strenght	> 200.000 cycles / 1.000 N	EN 1728:2000 - EN 15373:2007 - 3rd severe level
Lightfastness	8 - max. val.	EN ISO 4892-2/06 - co 4202, 0108, 4104, 1100, 2116
Color fastness to rubbing	5 - max. val.	EN ISO 105-x12:2003 - co 4165 1101 2102, 4154, 4104, 1195
Abrasion resistance	> 100.000 cycles	Martindale EN ISO 12947-2:1998
	■ Composition	
Warp yarn	4.700 dtex	
Weft yarn	4.700 dtex	
	■ Fabric components	
PVC COMPOUND	77%	
PES	23%	
	■ Management system	
Quality		ISO 9001
	■ Certifications, labels, warranties, recyclability	



CORPORATE QUALITY MANAGEMENT SYSTEM CERTIFICATION

