

# PVC COATED TARPAULIN

## DATA SHEET

FRT9850BL

Testing Method

|                              |                                                                          |                                               |
|------------------------------|--------------------------------------------------------------------------|-----------------------------------------------|
| Width                        | 300 cm<br>118 inch                                                       |                                               |
| Base Fabric                  | 100%PES<br>1100 Dtex 9x9                                                 | DIN EN ISO 2060                               |
| Total Weight                 | 800 g/m <sup>2</sup><br>23.53OZ/YD <sup>2</sup>                          | DIN EN ISO 2286-2<br>BS 3424 Method 5A        |
| Composition Fabric           | 200 g/m <sup>2</sup><br>5.9 OZ/YD <sup>2</sup>                           | DIN EN ISO 2286-2<br>BS 3424 Method 5B        |
| Composition Coating          | 600 g/m <sup>2</sup><br>17.63 OZ/YD <sup>2</sup><br>PVC+Acrylic+Blockout |                                               |
| Lacquering                   | 1/1                                                                      |                                               |
| Breaking Strength Warp       | 3000 N/5cm<br>675 LBS/2inch                                              | DIN 53 354<br>BS 3424 Method<br>FS 5100       |
| Breaking Strength Weft       | 2800 N/5cm<br>630 LBS/2inch                                              | DIN 53 354<br>BS 3424 Method<br>FS 5100       |
| Tear Strength Warp           | 300 N<br>67 LBS                                                          | DIN 53 363<br>BS 3424 Method<br>FS 5134       |
| Tear Strength Weft           | 300 N<br>67 LBS                                                          | DIN 53 363<br>BS 3424 Method<br>FS 5134       |
| Adhesion                     | 100 N/5cm<br>22.5 LBS/2inch                                              | DIN 53 357<br>BS 3424 Method 9B<br>FS 5970    |
| Temperature resistance       | -30°C/+70°C                                                              | DIN EN 1876-2<br>BS 3424 Method 10<br>FS 5874 |
| Light Fastness(except white) | 7-8                                                                      | DIN EN ISO 877<br>BS 3424 Method 15           |
| Flammability                 | Normal FR                                                                | DIN 75200<br>NFPA-701<br>CSFM Section 13115   |
| Application                  | Optional                                                                 |                                               |

ISO9001-2015

All our technical characteristics are indicative